



Biological Assessment Using Nanoparticles

Muneera DF ALKahtani*

Princess Nourah Bint Abdulrahman University, Riyadh, Kingdom of Saudi Arabia, Saudi Arabia

*Corresponding Author: Muneera DF ALKahtani, Princess Nourah Bint Abdulrahman University, Riyadh, Kingdom of Saudi Arabia, Saudi Arabia.

Received: March 25, 2019; Published: August 06, 2019

Abstract

Objectives: The increase of foods infected with microbes such as grain and stored seeds of the most important things that pose a global threat and there was an urgent need to use effective and safe antimicrobial and the use of nanoparticles to combat microbial pathogens are of increasing interest. In this study was used *Aspergillus Niger* to reduce Silver nitrate salt in nanoparticle particles (AgNPs).

Methods: Production conditions were 100 milliliters of silver nitrate at 28°C and pH 5.5.

Result: AgNPs the concentration of adsorption at the plasma surface of the silver particles, which was shown in silver color, changed the color of leachate from red to condensed milk after 24 hours of incubation. The filtration without AgNP was found to have no change in color. AgNP was observed by TEM spherical and smooth with sizes of 20-100 nm. "Infrared spectroscopy" was used, and an RI analysis was accomplished. The result was the release of the proteins in the leachate and dictated by the reduction of the silver ions present in the solution. In SEM imaging, direct effects were found on multicellular cytotoxicity and detecting large amounts of *P. aeruginosa* and *S. aureus* cells interacting with AgNPs unlike nature showed a smooth surface.

Biological activity was recorded against *Aspergillus flavus*, *Candida albicans*, *Bacillus cereus*, *pseudomonas aeruginosa*, *Escherichia*, *Escherichia coli*, *Staphylococcus aureus*.

In optimal conditions with a bacterial test that showed low sensitivity to concentrations (AgPNs) with MICs of 5, 10, 11, 8, 7, 7 and 10 ml, respectively.

Conclusion: Here through the inhibitory sub-concentrations of AgNPs the BIO film was successfully formed by bacterial pathogens that were tested and the effect of cytotoxicity and anti-tumor activity. The result confirmed that the sensibility of the human cancer cell line to AgNPs was higher than the Vero cell line at the same dose level of AgNPs.ace.

Keywords: Fungi; biosynthesis; AgNPs; TEM; HepG-2; MCF-7; Biofilm

Introduction

Nanoparticles are known to have at least one dimension of 100 nm [1].

Their chemical composition contains bio-degradable or toxic agents [2,3].

Therefore, environmentally friendly alternatives have been used to produce chemicals such as manufacturing through biological synthesis, sought. Several studies have reported that microorganisms, plants and fungi can create nanoparticles through biological pathways [4-6]. It has been discovered that pathogenic and non-

pathogenic fungi are capable of the bio-composition of nanoparticle particles [7].

Many authors have used a variety of fungal isolates to produce silver nanoparticles (AgNPs) from silver nitrate salt, both extracellularly and intracellularly Khan., *et al.* [8] and Zhao., *et al.* [9] including (*Fusarium oxysporum*) [10], (*F. semitectum*) [11] (*Aspergillus fumigates*) [12], (*A. niger*) [13], (*A. clavatus*) [14], (*Penicillium brevicompactum*).

Siddiqi., *et al.* [15] (*Cladosporium cladosporioides*). used fungi as a good model for nanoparticle synthesis and is the best among oth-

er microorganisms. and the disorder in its use is complex in growth essentials, but it is easy to manufacture. For fungi, exogenous secretions contain reductive proteins, so nanoparticles are deposited externally and free of materials Which allows for direct use of various applications. [16]. It has been established that AgNPs possess antimicrobial activity [17]. *In vitro* cytotoxicity analysis techniques decrease the use of these tissues and cells that have been increased [18,19]. At present, the biological evaluation of nanoparticles has been carried out using fungi and has given encouraging results against both bacteria, fungi and cancer cells. Currently, our food is more contaminated than it ever was. Due to the increasing use of pesticides, we may find ourselves facing a dangerous threat against mankind. This threat is called Bacteria.

Materials and Methods

Microbial species

A. niger, *A. flavus*, *candida albicans* and Gram-positive bacteria, *B. cereus*, *Staphylococcus aureus* and Gram-negative bacteria, *Escherichia coli*, *Pseudomonas* and *S. typhi*. were all collected from the Department of Microbiology at King Faisal Specialist Hospital, Riyadh City, Saudi Arabia., These bacteria were utilized for bioactive study of silver nanoparticles (AgNPs) (from 2016 to 2017).

Biosynthesis of agNPs

A. niger was inoculated in 500 ml Erlenmeyer flasks containing 100 ml of MGYP medium, composed (g/L) of malt extract (3g), glucose (10g), yeast extract (3g), and peptone (5g) and incubated at 25–28°C under shaking conditions (200 rpm) for 4 days. After incubation, mycelia were collected from the culture broth by centrifugation at 5000 rpm for 20 min and washed with sterile distilled water. Ten grams of mycelial mass was re-suspended in 100 ml of AgNO₃ solution in 500 ml Erlenmeyer flasks at pH 5.5, and shaken at 28°C (200 rpm) for 72 h. The AgNPs bio-transformation was routinely monitored by measuring the solution's change in color. Centrifugation was performed at a comfortable temperature range in doors at 14,000 rpm for 30 minutes, after which the AgNPs solution was resuspended in 1ml sterile water.

UV-visible spectroscopy analysis

Changes in absorption of the filtrate were measured after 24h using a UV-visible spectrophotometer (Milton-Roy Spintronic 1201). Measurements were also performed after several weeks in to check the stability of synthesized AgNPs.

Transmission electron microscopy (TEM)

For TEM analysis, a drop of cell filtrate was placed on "carbon-coated" copper grids, and then dried by evaporation at room temperature. A GEOL GEM-1010 transmission electron microscope was utilized to acquire electron micrographs at 70 kV at the Regional Centre for Mycology and Biotechnology (RCMB) [20].

X-ray analysis (EDX)

The existence of elemental silver was established through EDX using an X-ray microanalyzer, (Oxford 6587 INCA) and a JEOL JSM-5500 LV scanning electron microscope at 20 kV. The EDX spectrum was recorded in spot profile mode from one of the most densely populated silver nanoparticles regions on the film exterior. The Nano crystallites were examined by a Quanta 200 FEG [21].

Scanning electron microscope (SEM)

Bacterial cultures were patronized with AgNPs at concentration of 50 ppm, and incubated for 24h at 30°C. The samples were treated with glutaraldehyde (2.5%) and dehydrated by sequent dilution in ethanol using an automatic tissue processor (Leica EM TP) Next, the samples were dried using a CO₂ critical point drier (Tousimis Audosamdri-815). The samples then "gold coated" SPI-model sputter coater. The samples were examined by scanning electron microscopy (JEOL-JSM-5500LV).

Bacteriological assessments

AgNPs were assessed for antimicrobial activity against pathogenic microorganisms.

Disc diffusion assay

Wells were created in nutrient agar plates inoculated with bacteria using sterilized cork borer and impregnated with 100 µL/well AgNPs. Sabouraud Dextrose Agar (SDA), was inoculated with tested fungi before the agar solidification. Wells were cut into the plates using A cork borer, and 50 µL of AgNP solution was dispensed in each well. Negative controls were set up u by sterile distilled water according to the prescribed protocol [22]. Then, plates were incubated at 37°C for 24h for bacteria, and 28°C for 4days for fungi. Microbial susceptibility was estimated by measuring the diameters of the zones of inhibition, with values recorded as the average of three replicates (NARMS, 2002). The percentage of microbial growth reduction (GR%) was estimated using the broth micro dilution method, with the control treatment referenced as: $GR\% = (C-T)/Cx100$. Where, C is the cell concentrations under the control treatment and T is replicates the results were recorded as means ± SE of the triplicate experiment [22].

Determination of Minimum Inhibitory Concentration (MIC)

The lowest concentration of AgNPs resulting in inhibition of bacterial or fungal growth was determined by the broth micro dilution method, and recorded as the MIC [22].

Anti-virulence activity tests

Biofilm Formation and Inhibition Assays

Bacterial strains were tested for their capability to form biofilms by means of the tissue culture plate assay, as described by (Christensen., *et al.* 1995).

The AgNPs was tested for their potential to prevent bacterial biofilm formation at sub-MIC concentration against tested bacterial isolates, according to the method of (Lin., *et al.* 2011).

Evaluation of the antitumor activity

Monolayer microtiter plates of HepG2 and normal Vero cells were obtained from The Egyptian Organization for Biological Products and Vaccine Production (VACSERA). The monolayer cells were treated with 40, 50, 60, and 70 ppm AgNPs in fresh conservation medium and incubated at 37°C. The microtiter plates were then stained with crystal violet [23]. The number of the surviving cells was determined using an ELISA reader (Sun Rise, TECAN, Inc, USA) at 490 nm after well blending. The viability percentage was calculated as $1 - (\text{ODt}/\text{ODc}) \times 100\%$, where ODt is the mean optical density of wells patronized with AgNPs and ODc is the mean optical intensity of untreated cells. The 50% inhibitory concentration (IC50) which is the concentration required to cause toxic effects in 50% of intact cells, was predestined from graphic plots.

Results

Biosynthesis of AgNPs

A. niger succeeded in reducing silver salt into silver Nanoparticles. AgNP formation resulted in the color of the culture filtrate changing from an intense red to brown after 24 h of incubation, while the culture filtrate without silver nitrate salt did not demonstrate any color change (Figure 1). Smooth surfaced spherical AgNP with sizes of 20 to 100 nm were observed by TEM (Figure 1). AgNPs were determined to have a poly dispersity index < 0.450 using Zeta-sizer analysis. Zeta ability showed the surface of AgNPs have positive charges around 35.5 mV.

Infrared spectroscopy analysis

IR analysis was performed to characterize the chemical temple of AgNPs. The filtrate of silver nitrate patronize *A.niger* with the solution showed the surface plasmon absorption at 280 and 420




Figure 1: Photo tube gram showing color change observed in fungal extract of *A. niger* with silver nitrate solution (A). The control without silver nitrate salt did not exhibit any color change after 24 h incubation. Micrograph (B) showing the AgNPs biosynthesized by *A. Niger*. Scale bar = 100 nm using TEM.

SEM imaging

SEM observations confirmed the direct effects of AgNPs on cubicle morphology, revealing the effects of considerable amounts of cellular damage (Figure 1). Gram-negative *P. aeruginosa* and Gram-positive *S. aureus* cells treated back AgNPs appeared lean regarding weird stall walls and were surrounded by cellular snip-pet in comparison normal cells (control) were intact and showed a smooth surface (Figure 2,3).




Figure 2: Electro micrograph showing morphological alterations in *P. aeruginosa* and *S. aureus* bacteria exposed to AgNPs. Controls are untreated bacteria. Scale bars are 2 μ m.




Figure 3: Cell line images, showing effect of AgNPs at different concentrations (C1, C2, and C3) for 24 h on HepG-2, MCF-7 and Vero cell lines comparable to control.

nm was combined with tryptophan and tyrosine residues present in the protein. This result was observed the proteins was released into filtrate and indicated the reduction of silver ions present in the solution.

Antimicrobial activity testing

AgNPs exhibited moderate antimicrobial activity zones of inhibition opposed to *C. albicans* 15.7mm, and Gram-positive *B. cereus* 14.5mm, and *S. aureus* 13.2 mm, High antimicrobial activity with zones of inhibition was seen opposed to *A. flavus* 18.5mm, *E. coli* 20.4mm, *P. aeruginosa* 19.2mm, and *S. typhi* 21.2 mm, (Table 1) The median inhabitation was for *A. flavus* 45.65, and *C. albicans* 74.65, Gram-positive *B. cereus* 75.13 and *S. aureus* 81.6, Gram-negative *E. coli* 86.56, *P. aeruginosa* 92.25, and *S. typhi* 72.15. The MICs of AgNPs 50 ppm opposed to the probed bacteria growth at

condensation, *A. flavus* 5mL-1, *C. albicans* 11mL-1, Gram-positive *B. cereus* and *S. aureus* 10mL-1, gram negative *E. coli* 8mL-1, *P. aeruginosa* and *S. typhi* 7mL-1.

Amid seven tested microbial isolates, the rugged biofilm producing by isolates *B. cereus* 0.74., *P. aeruginosa* 0.56, *S. aureus* 0.64, and *S. typhi* 0.55, with optical densities. In contrast, moderate biofilm was featured by *C. albicans*, *E. coli*, *P. aeruginosa*, and *S. aureus*, apropos ODs of 0.45 and 0.35, and weak biofilm producing by *A. flavus* (0.25 O.D.). Biofilm deactivation was investigated for ability to prevent biofilm figuration by powerful biofilm producing bacterial isolates (*P. aeruginosa* and *S. aureus*) grown with far different sub (MICs) concentrations. The results showed that deactivation of biofilm formation by AgNPs of *A. flavus* 75.45, *C. albicans* 70.25, gram positive *B. cereus* 64.72, and *S. aureus* 87.23, gram negative *E. coli*

Microbial isolates							
Assessments	fungi		Gram positive		Gram negative		
	<i>A. flavus</i>	<i>C. albicans</i>	<i>S. aureus</i>	<i>B. cereus</i>	<i>E. coli</i>	<i>Ps. aeruginosa</i>	<i>S. Typhi</i>
GI (mm)	18.5	15.7	13.2	14.5	20.4	19.2	21.2
MGI	45.65	74.65	81.6	75.13	86.56	92.25	72.15
MICs (mL/L)	5	11	10	10	8	7	7
Biofilm formation	0.25	0.45	0.64	0.74	0.32	0.56	0.55
Biofilm reduction (%)	75.45	70.25	87.23	64.72	67.85	78.44	75.50
Chi-Square	0.18						
DF	2						
P-Value	0.9146						

Table 1: The diameter of zones of inhibition, mean growth inhibition percentages, MGI and Minimum Inhibitory Concentrations of AgNPs MICs against pathogenic bacteria and fungi. AgNPs were applied at 50 ppm (2 mL/L). Each value is the mean of 3 replicates. by ELISA plate reader.

67.85, *P. aeruginosa* 78.44, and *S. typhi* 75.50% at the condensation tested (Table 1). Biological activity counted by diameter zones of suppression was registered against these organisms; *Aspergillus flavus*, *Escherichia*, *Candida albicans*, *Bacillus cereus*, *pseudomonas aeruginosa*, *Escherichia coli*, *Staphylococcus aureus*. Figure 4 and 5, (Table 1) shows the summary of the biological activity, overall gram-positive gram bacteria had the highest reduction percentage. No effect of organism was recorded ($P < 0.05$).




Figure 4: Boxplots of the diameter zones of inhibition by pathogens type for; A) Mean growth inhibition percentages, B) MGI and Minimum Inhibitory Concentrations of AgNPs, C) Biofilm Formation, D) MICs(mL/L).




Figure 5: Boxplots for the biofilm reduction percentage by pathogen types. Gram positive bacteria has the highest reduction percentage, followed by gram negative, and lastly fungi.

In optimal conditions with bacterial testing showed weak sensitivity of condensation (AgPNs) with MICs of 5, 10, 11, 8, 7, 7 and 10 ml respectively. The inhibitory sub-concentrations of AgPNs successfully form the BIO film by bacterial pathogens that have been tested. The anti-tumor and cytotoxic effect of the cytotoxicity signal results in the case related to the cell of cancer at the same dose level. Overall the most sensitive cell lines to AgPNs was MCF-7, followed by Hep-G2 and vero cell lines (Figure 6 and Table 2).

AgNPs conc. (ppm)	Viability %		
	(HepG-2)	(MCF-7)	Vero cell
70	40.75	25.85	90.75
60	70.25	65.45	95.25
50	75.65	70.12	100
40	83.36	85.56	100
0	100	100	100
	5 µg/mL	5 µg/mL	-
Cell Lines		Chi-Square	5.12
DF		2	
P value		0.08	
Concentrations (AgPNs)		Chi-Square	7.30
DF		4	
P value		0.12	

Table 2: Antitumor activity of AgNPs on Viability of against (HepG-2), (MCF-7) and Vero cell line.

Human hepatocellular carcinoma cell-line (HepG-2). Breast carcinoma cell-line (MCF-7). African green monkey kidney continuous cell line (Vero clone CCL-81).




Figure 6: Antitumor activity of AgNPs on Viability of by against (HepG-2), (MCF-7) and Vero cell lines.

Discussion

Currently, our food is more contaminated than it ever was.

Pathogenic bacteria can cause hundreds maybe even thousands of diseases, some of them can't be cured. Furthermore, you can try several ways to get rid of antimicrobial effects of antibiotics used to get rid of them. In this case, we are in a huge need to a new antibiotic which can't be resisted by bacteria, Silver nanoparticles (AgNPs) emerged as replacement to antibiotics because of its distinguished properties.

Silver nanoparticles made by green chemistry offer a potentially new alternative to chemically formed nanoparticles.

In this review, we will talk about the latest developments in the manufacture of nanoparticles, their implementation as antimicrobial agents and the mechanism of antimicrobial action [24].

Generally, the synthesis of nanoparticles has been carried out using three techniques, including physical, chemical, and biological methods. Silver nanoparticles are manufactured using physical methods by condensation and evaporation by an atmospheric tubular heater pressure. The advantages of physical methods are speed, radiation used as reducing agents, and no Evolution in the category of dangerous chemicals, in contrast the negative aspects are: pollution of solvents, high consumption of energy, low yield, and lack of uniform distribution [25].

Chemical methods use water or organic solvents to prepare the silver nanoparticles. This process employs three components, such as metal precursors, reducing agents, stabilizing/capping agents. Physical methods have no major advantage, such as high-yielding chemical methods. Expensive are those methods that I mentioned earlier. Additionally, the materials used for AgNPs synthesis, such as citrate, borohydride, and 2-mercaptoethanol are toxic and hazardous. Ignoring defects, the silver particles manufactured are not the purity required. Moreover, by conducting assembly, excludes many dangerous and toxic by-products out. Recently, Abbasi, *et al.* explained a detailed account of synthesis methods, properties, and bio-application of AgNPs [26].

To overcome the shortcomings of chemical, biological methods have Other solutions have emerged. Recently, biologically-mediated synthesis of nanoparticles has been shown to be simple, cost effective, dependable, approaches and much attention has been given to the high yield production of AgNPs. Bio-sorption of metals by Gram-negative and Gram-positive bacteria provided an indication for the synthesis of nanoparticles before the flourishing of this biological method. Several studies reported the synthesis of AgNPs using green, cost effective, and biocompatible methods without the

use of toxic chemicals in biological methods. In this green chemistry approach, several bacteria, including *Pseudomonas stutzeri* AG259, *Lactobacillus* strains, *Bacillus licheniformis*, *Escherichia coli* (*E. coli*), *Brevibacterium case*, fungi including *Fusarium oxysporum* were utilized. The major advantage of biological methods is the availability of amino acids, proteins, or secondary metabolites present in the synthesis process, the elimination of the extra step required for the prevention of particle aggregation, and the use of biological molecules for the synthesis of AgNPs is eco-friendly and pollution-free.

Maximum nanoparticle synthesis occurred when AgNO_3 was supplied at 30.75 mM in the reaction mixture, followed by the addition of 0.5 mM AgNO_3 . This can be demonstrating on the basis of enzyme-substrate kinetics; i.e. the key biomolecules active site which causes the process of reduction is previously saturated with the silver ions, and there's no available sites for additional ions to become reduced, and so, no further increase in AgNPs synthesis is possible, despite the presence of additional salt substrate [27].

Optimized parameters resulted in an increase in AgNP size and poly dispersity, as it was also found by Mulvaney [28] and Singh, *et al.* [27]. In this study, and at optimized conditions, the enhanced rate of production of AgNPs may be the direct result of the silver ions' effect as a substrate, pH, and temperature on a key biomolecule responsible for the process of reduction that occurs in the aqueous filtrate of *A. niger*. (Guzmán., *et al.* 2019).

In the present study, silver nanoparticles occur a mild antibacterial activity against *C. albicans*, *A. flavus*, and *S. aureus* with large areas of suppression, but antimicrobial activity is high against *B. cereus*, *E. coli*, *P. aeruginosa*, and *S. Typhoid*. Areas were suppression of growth 15.7, 14.5, and 13.2 mm respectively High antimicrobial activity was seen against *A. flavus*, *E. coli*, *P. aeruginosa*, and *S. typhi*, with zones of suppression of 18.5, 20.4, 19.2 and 21.2 mm, respectively The mean growth in habitation was 45.65, 75.13, 74.65, 86.56, 92.25, 81.6, and 72.15 OD for *A. flavus*, *B. cereus*, *C. albicans*, *E. coli*, *P. aeruginosa*, *S. aureus*, and *S. typhi* enterica, respectively.

A. niger succeeded in reducing silver salt in nanoparticles, *niger* with the solution showed that surface plasmon uptake at 280 and 420 nm was combined with tryptophan and tyrosine residues present in the protein.

The MICs of AgNPs (50 ppm) against the tested bacteria growth at concentrations, 5, 10, 11, 8, 7, 10, and 7 mL-1 respectively. (Guzmán., *et al.* 2019). It is well known that Ag ions and Ag-based compounds have biological activities [29,30].

Owing to their small size, AgNPs impair the sulphur and phosphorus containing essential macromolecules such as proteins and DNA [31]. Thus, action of AgNPs appears to be a consequence of adherence to and penetration inside the cell of the target cells.

Nanoparticles have been developed as image-capture agents, which can be specifically grouped into tumors and avoid tissue damage. Heat can lead to different types of cell death, depending on many factors, which can activate opposition responses. Some of them are desirable, such as induction of a specific immune response that can help eliminate the tumor, but others are best avoided, such as induction of cell growth and inflammation (Mattos., *et al.* 2014).

Silver ions are used in many types of formulations, and it was recently shown that AgNPs hybridized to amphiphilic hyperbranched macromolecules can be used to create effective antimicrobial surface coatings. The most significant application of silver and AgNPs is in production of medical supplies, such as topical ointments to protect from infection in burns and open wounds.

Newly devised AgNP-coated wound coverings have been innovation in the management of wounds or infections [32].

To stop or diminish infections, a novel generation of bandages incorporating antimicrobial agents, such as silver, has been commercialized. wound coverings impregnated with colloidal silver lead to a good reduction of pathogen-specific alterations in epithelium infection (Mordorski., *et al.* 2017).

The application of silver and AgNPs to infected keratinocytes in a moist healing environment is effective, active compared to wound coverings without silver. Similar outcomes with *E. coli* were attained with AgNPs [33,34]. The enhanced cytotoxicity achieved by AgNPs may be attributed to their size, which assists with penetration into tumor cells.

Other researchers have suggested that AgNPs may interfere with active sites of cellular proteins, subsequently cellular chemistry (Behzadi., *et al.* 2017).

Therefore, it is probable that once they penetrate cells, AgNPs may attack functional proteins of cells, leading to partial aggregation and unfolding of proteins, as has been found in the case of bovine hemoglobin.

Toxicity of silver nanoparticles is concentration, size, and shape dependent (Shashi., *et al.* 2017).

In this study, we used different intervals of time to find out whether the antibacterial effect of GC-AgNps was bacteriostatic or bactericidal.

The antibacterial test was measured by the MIC using different concentrations of GC-AgNps. The MIC for *E. coli* as a model of Gram-negative bacteria was 1 µg/mL after 120min of exposure with GC-AgNps and enough to inhibit 99.8% of growth. Therefore, ME at 1 µg/mL showed < 2.71 in which the bacteria at this level did not present viable cells to count. In contrast, the ABE exhibited that concentrations of 0.1 and 0.01 µg/mL were insufficient to inhibit growth [35-61].

Conclusion

In conclusion, it was found that the silver particles have a positive effect against microbes and cancer cells. We reached to this result after the silver particles were extracted and conducted many experiments on them. On the other hand, silver particles are harmless to the nature as opposed to other materials for that reason silver particles were popular in the medical field.

Acknowledgments

We take our pleasure in expressing our sincere thanks to Abrar saeed al ayoubi, Nada khalid alobaid, Nouf Abdullah aljumah and Tahani Alwi Doshi.

Bibliography

1. Nanjwade BK., *et al.* "Design and Characterization of Nanoparticulate Drug Delivery". In *Characterization and Biology of Nanomaterials for Drug Delivery* Elsevier (2019): 337-350.]
2. Ghorbani HR., *et al.* "Biological and nonbiological methods for silver nanoparticles synthesis". *Chemical and Biochemical Engineering Quarterly* 25.3 (2011): 317-326.
3. Arif N., *et al.* "Current trends of engineered nanoparticles (ENPs) in sustainable agriculture: An overview". *Journal of Environmental and Analytical Toxicology* 6 (2016): 1-5.
4. Abou El-Nour KMM., *et al.* "Synthesis and application of silver nanoparticles". *Arabian Journal of Chemistry* 3.3 (2010): 135-140.
5. Popescu M., *et al.* "Biogenic production of nanoparticles". *Digest Journal of Nanomaterials and Biostructures* 5.4 (2010): 1035-1040.
6. Khan HI., *et al.* "Facile synthesis of gold nanostars over a wide size range and their excellent surface enhanced Raman scattering and fluorescence quenching properties". *Journal of Vacuum Science and Technology* 36 (2018): 03E101.
7. Fait ME., *et al.* "Cationic surfactants as antifungal agents". *Applied microbiology and biotechnology* 103.1 (2019): 97-112.
8. Khan S., *et al.* "Concurrent biomineralization of silver ions into Ag⁰ and Ag₂O by *Leptolyngbya* strain JSC-1 and the establishment of its axenic culture". *Chemosphere* 215 (2019): 693-702.]
9. Zhao X., *et al.* "Fungal silver nanoparticles: Synthesis, application and challenges". *Critical Reviews in Biotechnology* 38.6 (2017): 817-835.
10. De Souza TAJ., *et al.* "Silver nanoparticles: An integrated view of green synthesis methods, transformation in the environment, and toxicity". *Ecotoxicology and environmental safety* 171 (2019): 691-700.]
11. Allam Nanis G., *et al.* "Biosynthesis of silver nanoparticles by cell-free extracts from some bacteria species for dye removal from wastewater". *Biotechnology Letters* 41.3 (2019): 379-389.]
12. Joshi SR and Kalita D. "Biological, Chemical and Nanosorption Approaches in Remediation of Metal Wastes". In *Remediation Measures for Radioactively Contaminated Areas* (2019): 93-111.
13. Verma VC., *et al.* "Biosynthesis of antimicrobial silver nanoparticles by the endophytic fungus *Aspergillus clavatus*". *Nanomedicine (Lond)*. 5.1 (2010): 33-40.
14. Banerjee K and Rai VR. "A review on mycosynthesis, mechanism, and characterization of silver and gold nanoparticles". *Bio Nano Science* 8.1 (2018): 17-31.]
15. Siddiqi KS and Husen A. "Fabrication of metal nanoparticles from fungi and metal salts: scope and application". *Nanoscale Research Letters* 11.1 (2016): 98.]
16. Narayanan KB and Sakthivel N. "Biological synthesis of metal nanoparticles by microbes". *Advances in Colloid and Interface Science* 156.1-2 (2010): 1-13.

17. Ahmed F, *et al.* "Benign nano-assemblages of silver induced by β galactosidase with augmented antimicrobial and industrial dye degeneration potential". *Materials Science and Engineering C* 91 (2018): 570-578.
18. Byrd D, *et al.* "Phrasal signatures in articulation. In: Papers in Laboratory Phonology V. Acquisition and the Lexicon. Edited by M.B. Broe and J.B. Pierrehumbert. (Cambridge University Press) (2002): 70-87.
19. Noha K, *et al.* "Evaluation of silver nanoparticles as antiviral agent against ToMV and PVY in Tomato Plants". *Middle East Journal of Applied Sciences* 8.1 (2018): 100-111.
20. Jain N, *et al.* "Extracellular biosynthesis and characterization of silver nanoparticles using *Aspergillus flavus* NJP08: a mechanism perspective". *Nanoscale* 3.2 (2011): 635-641.
21. Devi JS, *et al.* "In vitro anticancer activity of silver nanoparticles synthesized using the extract of *Gelidiella* sp". *International Journal of Pharmacy and Pharmaceutical Sciences* 4.4 (2012): 710-715.
22. NCCLS/CLSI. Performance Standards for Antimicrobial Susceptibility Testing; Seventeenth Informational Supplement Replaces M100-S16 26 (2007): 3.
23. Mosmann T. "Rapid colorimetric assay for cellular growth and survival: application to proliferation and cytotoxicity assays". *Journal of Immunological Methods* 65.1-2 (1983): 55-63.
24. Titirici M and Antonietti M. "Chemistry and materials options of sustainable carbon materials made by hydrothermal carbonization". *Royal society of chemistry* 39 (2010): 103-116.
25. Ahmed S and Sikram S. "One Pot Green Synthesis Using *Terminalia arjuna* Extract for Biological Application". *Silver Nanoparticles* 6 (2015): 309.
26. Abbasi T, *et al.* "Gainful utilization of the highly intransigent weed *ipomoea* in the synthesis of gold nanoparticles". *Journal of King Saud University* 27.1 (2015): 15-22.
27. Singh R, *et al.* "Synthesis, optimization, and characterization of silver nanoparticles from *Acinetobacter calcoaceticus* and their enhanced antibacterial activity when combined with antibiotics". *International Journal of Nanomedicine* 8 (2013): 4277-4290.
28. Mulvaney P. "Surface plasmon spectroscopy of nanosized metal particles". *Langmuir* 12.3 (1996): 788-800.
29. Furno F, *et al.* "Silver nanoparticles and polymeric medical devices: A new approach to prevention of infection?". *Journal of Antimicrobial Chemotherapy* 54.6 (2004): 1019-1024.
30. Anugrah Y, *et al.* "Independent gate control of injected and detected spin currents in CVD graphene nonlocal spin valves" *AIP Advances* 8 (2018): 015129.
31. Hany Mohamed and Mourad Marwa. "Biosynthesis of Silver Nanoparticles Using Fungi and Biological Evaluation of Mycosynthesized Silver Nanoparticles". *The Egyptian Society of Experimental Biology* 10 (2014): 1-12.
32. Sadasivuni K, *et al.* "Silver Nanoparticles and Its Polymer Nanocomposites Synthesis, Optimization, Biomedical Usage, and Its Various Applications". *Spriger link* (2019): 331-373.
33. Devi LS and Joshi SR. "Antimicrobial and synergistic effects of silver nanoparticles synthesized using soil fungi of high altitudes of eastern Himalaya". *Mycobiology* 40.1 (2012): 27-34.
34. Mudasir AD, *et al.* "Enhanced antimicrobial activity of silver nanoparticles synthesized by *Cryphonectria* sp. evaluated singly and in combination with antibiotics". *Nanomedicine* 9.1 (2013): 105-110.
35. Cho KH, *et al.* "The study of antimicrobial activity and preservative effects of nanosilver ingredient". *Electrochimica Acta* 51.5 (2005): 956-960.
36. Elechiguerra JL, *et al.* "Interaction of silver nanoparticles with HIV-1". *Journal of Nanobiotechnology* 3 (2005): 6.
37. Gudikandula K, *et al.* "Biogenic synthesis of silver nanoparticles from white rot fungi: Their characterization and antibacterial studies". *OpenNano* 2 (2017): 64-78.
38. Gangadevi V and Muthumary J. "Preliminary studies on cytotoxic effect of fungal taxol on cancer cell lines". *African Journal of Biotechnology* 6 (2007): 1382-1386.
39. Ingle A, *et al.* "Mycosynthesis of silver nanoparticles using the fungus *Fusarium acuminatum* and its activity against some human pathogenic bacteria". *Current Nanoscience* 4.2 (2008): 141-144.

40. Ingrid José Mauricio. "Dimorphism and allometry of *Systalotercus platyrhinus* and *Hypselotropis prasinata*". *Researchgate* 31.1 (2014): 51-62.
41. Kathiresan K., et al. "Studies on silver nanoparticles synthesized by a marine fungus, *Penicillium fellutanum* isolated from coastal mangrove sediment". *Colloids and Surfaces B* 71.1 (2009): 133-137.
42. Katherine., et al. "Progress in Organic Coatings". *Elsevier* (2019): 1-366.
43. Khatoun N., et al. "Synthesis and spectroscopic characterization of gold nanoparticles via plasma-liquid interaction technique". *AIP Advances* 8 (2018): 015130.
44. Lok CN., et al. "Proteomic analysis of the mode of antibacterial action of silver nanoparticles". *Journal of Proteome Research* 5.4 (2006): 916-924.
45. Lakshmanan G., et al. "Plant-mediated synthesis of silver nanoparticles using fruit extract of *Cleome viscosa* L: Assessment of their antibacterial and anticancer activity". *Karbala International Journal of Modern Science* 4.1 (2018): 61-68.
46. Liu J., et al. "Magnetic nanocomposites with mesoporous structures: Synthesis and applications". *Small* 7.4 (2011): 425-443.
47. Magdi HM., et al. "Biosynthesis of silver nanoparticles using fungi and biological evaluation of mycosynthesized silver nanoparticles". *Egyptian Journal of Experimental Biology (Bot.)*, 10.1 (2014): 1-12.
48. Morones JR., et al. "The bactericidal effect of silver nanoparticles". *Nanotechnology* 16.10 (2005): 2346-2353.
49. NCCLS. Performance Standards for Antimicrobial Susceptibility Testing, 12th Informational Supplement M100-S12, National Committee for Clinical Laboratory Standards, Villanova, PA (2002).
50. Okafor F., et al. "Green synthesis of silver nanoparticles, their characterization, application and antibacterial activity". *International Journal of Environmental Research and Public Health* 10.10 (2013): 5212- 5238.
51. Panyala NR., et al. "Silver or silver nanoparticles: A hazardous threat to the environment and human health". *Journal of Applied Biomedicine* 6 (2008): 117-129.
52. Rogers JV., et al. "A preliminary assessment of silver nanoparticle inhibition of monkey pox virus plaque formation". *Nanoscale Research Letters* 3.4 (2008): 129-133.
53. Rajput S., et al. "Fungal isolate optimized for biogenesis of silver nanoparticles with enhanced colloidal stability". *Langmuir* 32.34 (2016): 8688-8697
54. Spagnoletti FN., et al. "Extracellular biosynthesis of bactericidal Ag/AgCl nanoparticles for crop protection using the fungus *Macroplasma phaseolina*". *Journal of Environmental Management* 231 (2019): 457-466
55. Shakibaie MR., et al. "Plasmid mediated silver and antibiotic resistance in *Acinetobacter baumannii* BL54". *Iranian Journal of Medical Sciences* 23 (1998): 30-36.
56. Singh S., et al. "Silver nanoparticles: Biomedical applications, toxicity, and safety issues". *International Journal of Research in Pharmacy and Pharmaceutical Sciences* (2017) 1-10.
57. Serpooshan V., et al. "Cellular uptake of nanoparticles journey inside the cell". *Chemical Society reviews* 46 (2017): 4218-4244.
58. Thomas V., et al. "A versatile strategy to fabricate hydrogel-silver nanocomposites and investigation of their antimicrobial activity". *Journal of Colloid and Interface Science* 315.1 (2007): 389-395.
59. Ur Rahman O., et al. "Lignin nanoparticles: Synthesis, characterization and corrosion protection performance". *New Journal of Chemistry* 42 (2018): 3415-3425.
60. Xie H., et al. "Efficient spin-current injection in single-molecule magnet junctions". *AIP Advances* 8 (2018): 015131.
61. Zhang H and Chen G. "Potent antibacterial activities of Ag/TiO₂ nanocomposite powders synthesized by a one-pot sol-gel method". *Environmental Science and Technology* 43.8 (2009): 2905-2910.

Volume 2 Issue 9 September 2019

© All rights are reserved by Muneera DF ALKahtani.